

CURRENT VERSION OF THE CLAIMS

The following listing of claims is the current version of the claims:

LISTING OF CLAIMS:

1. (Original): A polarizing plate having

a (single transmittance)/(crossed transmittance) > 600 when a wavelength is 440 nm;

a (single transmittance)/(crossed transmittance) > 3000 when a wavelength is 550 nm; and

a (single transmittance)/(crossed transmittance) > 11000 when a wavelength is 610 nm,

where single transmittance denotes optical transmittance of one polarizing plate and crossed transmittance denotes optical transmittance of two polarizing plates arranged so that the polarizing axes cross at right angles.

2. (Original): The polarizing plate according to claim 1, wherein the polarizing plate has

a (parallel transmittance)/(crossed transmittance) > 700 when a wavelength is 440 nm;

a (parallel transmittance)/(crossed transmittance) > 3000 when a wavelength is 550 nm; and

a (parallel transmittance)/(crossed transmittance) > 11000 when a wavelength is 610 nm,

where parallel transmittance denotes optical transmittance of two polarizing plates arranged so that the polarizing axes become parallel to each other, and crossed transmittance denotes optical transmittance of two polarizing plates arranged so that the polarizing axes cross at right angles.

3. (Currently amended): The polarizing plate according to claim 1, wherein a luminous corrected transmittance Y is at least 42.5% when ~~the~~ a standard illuminant is a C light source having luminous factor correction per 10 nm in a range from 700 nm to 400 nm.

4. (Currently amended): The polarizing plate according to claim ~~1~~ 3, wherein the

transmittance Y is at least 43.0% but not more than 44.0%.

5. (Original): The polarizing plate according to claim 1, wherein the polarization degree is at least 99.98%.

6. (Original): The polarizing plate according to claim 1, produced from a polyvinyl alcohol (PVA) film in a series of steps of:

dyeing the PVA film in a dye bath containing a dye selected from the group consisting of dichroic iodine and dichroic dyestuff, and crosslinking in at least two crosslinking baths containing a crosslinking agent while stretching the PVA film in the respective crosslinking steps, in which a stretch ratio in a first crosslinking bath is 1-4, and a stretch ratio in a second crosslinking bath is higher than the stretch ratio in the first bath.

7. (Original): The polarizing plate according to claim 6, wherein a total stretch ratio for the PVA film ranges from 5 to 7.

8. (Original): The polarizing plate according to claim 1, further comprising either a reflecting plate or a semitransparent reflecting plate bonded to the polarizing plate.

9. (Original): The polarizing plate according to claim 1, further comprising a retardation plate (λ plate) bonded to the polarizing plate.

10. (Original): The polarizing plate according to claim 1, further comprising a viewing angle compensating film bonded to the polarizing plate.

11. (Original): The polarizing plate according to claim 1, further comprising a brightness-enhanced film bonded to the polarizing plate by means of either an adhesive or pressure-sensitive adhesive.

12. (Original): A liquid crystal display comprising a liquid crystal cell and a polarizing

plate provided onto at least one surface of the liquid crystal cell,

wherein the polarizing plate obtained from a polyvinyl alcohol (PVA) film has
a (single transmittance)/(crossed transmittance) > 600 when a wavelength is 440 nm;
a (single transmittance)/(crossed transmittance) > 3000 when a wavelength is 550 nm; and
a (single transmittance)/(crossed transmittance) > 11000 when a wavelength is 610 nm;

where single transmittance denotes optical transmittance of one polarizing plate and
crossed transmittance denotes optical transmittance of two polarizing plates arranged so that the
polarizing axes cross at right angles.

13. (Original): A method of producing a polarizing plate, comprising:

dyeing a PVA film in a dye bath containing a dye selected from the group consisting of
dichroic iodine and dichroic dyestuff, and crosslinking in at least two crosslinking baths
containing a crosslinking agent while stretching the PVA film in the respective crosslinking steps,
in which a stretch ratio in a first crosslinking bath is 1-4 and a stretch ratio in a second crosslinking
bath is higher than the stretch ratio in the first bath;

the polarizing plate having

a (single transmittance)/(crossed transmittance) > 600 when a wavelength is 440 nm;
a (single transmittance)/(crossed transmittance) > 3000 when a wavelength is 550 nm; and
a (single transmittance)/(crossed transmittance) > 11000 when a wavelength is 610 nm;

where single transmittance denotes optical transmittance of one polarizing plate and
crossed transmittance denotes optical transmittance of two polarizing plates arranged so that the
polarizing axes cross at right angles.

14. (Original): The method according to claim 13, wherein the crosslinking agent is boric

acid.

15. (Original): The method according to claim 13, wherein a total stretch ratio for the PVA film ranges from 5 to 7.

16. (Original): The method according to claim 13, wherein the polarizing plate has
a $(\text{parallel transmittance})/(\text{crossed transmittance}) > 700$ when a wavelength is 440 nm;
a $(\text{parallel transmittance})/(\text{crossed transmittance}) > 3000$ when a wavelength is 550 nm; and
a $(\text{parallel transmittance})/(\text{crossed transmittance}) > 11000$ when a wavelength is 610 nm;

where parallel transmittance denotes optical transmittance of two polarizing plates arranged so that the polarizing axes become parallel to each other, and crossed transmittance denotes optical transmittance of two polarizing plates arranged so that the polarizing axes cross at right angles.

17. (Currently amended): The method according to claim 13, wherein a luminous corrected transmittance Y is at least 42.5% when the a standard illuminant is a C light source having luminous factor correction per 10 nm in a range from 700 nm to 400 nm.

18. (Currently amended): The method according to claim ~~16~~ 17, wherein the transmittance Y is at least 43.0% but not more than 44.0%.

19. (Original): The method according to claim 13, wherein the polarization degree is at least 99.98%.

20. (Previously presented): The polarizing plate according to claim 1, wherein the polarizing plate has

a $(\text{single transmittance})/(\text{crossed transmittance}) > 2306$ when a wavelength is 440 nm;

a $(\text{single transmittance})/(\text{crossed transmittance}) > 3948$ when a wavelength is 550 nm;

a (single transmittance)/(crossed transmittance) > 14500 when a wavelength is 610 nm.

21. (Previously presented): The polarizing plate according to claim 1, wherein the polarizing plate has

a (single transmittance)/(crossed transmittance) > 2192 when a wavelength is 440 nm;

a (single transmittance)/(crossed transmittance) > 43530 when a wavelength is 550 nm;

a (single transmittance)/(crossed transmittance) > 121760 when a wavelength is 610 nm.

22. (Previously presented): The polarizing plate according to claim 2, wherein the polarizing plate has

a (parallel transmittance)/(crossed transmittance) > 1799 when a wavelength is 440 nm;

a (parallel transmittance)/(crossed transmittance) > 3392 when a wavelength is 550 nm;

a (parallel transmittance)/(crossed transmittance) > 12503 when a wavelength is 610 nm.

23. (Previously presented): The polarizing plate according to claim 2, wherein the polarizing plate has

a (parallel transmittance)/(crossed transmittance) > 1714 when a wavelength is 440 nm;

a (parallel transmittance)/(crossed transmittance) > 37390 when a wavelength is 550 nm;

a (parallel transmittance)/(crossed transmittance) > 18745 when a wavelength is 610 nm.

24. (Previously presented): A method of producing a polarizing plate, comprising:

dyeing a PVA film in a dye bath containing a dye selected from the group consisting of dichroic iodine and dichroic dyestuff, and crosslinking in at least one crosslinking bath containing a crosslinking agent while stretching the PVA film in respective crosslinking steps in which a stretch ratio in a first crosslinking step is 1-4 and a stretch ratio in a second crosslinking step is higher than the stretch ratio in the first crosslinking step;

the polarizing plate having:

a (single transmittance)/(crossed transmittance) > 600 when a wavelength is 440 nm;

a (single transmittance)/(crossed transmittance) > 3000 when a wavelength is 550 nm;

a (single transmittance)/(crossed transmittance) > 11000 when a wavelength is 610 nm.